

Boedal

Typical Properties

Product name	Chemical name	CAS No	Density @ 20°C g/cm ³	Colour (H.U.)	Viscosity (ASTM D445) (mm ² /s)			Viscosity Index	Flash point °C COC	Pour point °C	Acid value (mgKOH/g)	SAP value (mgKOH/g)	Water (% W/W)	OECD301B
					20°C	40°C	100°C							
Cereplas 100XS	Di 2-ethylhexyl terephthalate	6422-86-2	0.982	<20	85.0	29.2	4.5	27	218	-69	0.01	280	0.02	-
Greenfad 2230	2EH Laurate	20292-08-4	0.86	<50	-	5.5	-	141	190	-30	0.1	-	-	-
Greenfad 2220	2EH Palmate	29806-73-3	0.86	<50	-	8.3	2.8	161	215	7	0.2	-	-	-
Greenfad 2216	2EH Stearate	22047-49-0	0.865	-	-	9	-	191	215	7	0.2	-	-	-
Greenfad 2200V	2EH Oleate	85049-37-2	0.87	-	-	8.0	-	214	225	-35	0.2	143	<0.1	-
Greenfad 2240	2EH Cocoate	92044-87-6	-	-	-	6.1	-	161	197	-28	0.1	-	-	-
Cereplas DOA	Di 2-ethylhexyl adipate	103-23-1	0.925	10	15	7.6	2.3	128	205	-63	0.01	306	0.05	-
Cereplas DIDA	Di isodecyl adipate	27178-16-1	0.918	20	27	13.5	3.5	148	223	-63	0.01	266	0.05	-
Cereplas DODA	Di isotridecyl adipate	26401-35-4	0.912	20	60	26.5	5.4	138	241	-57	0.01	225	0.05	81
Cereplas L8TM	Linear Octyl Trimellitate	89-04-3	0.983	50	120	44	7.1	121	268	-54	0.07	304	0.05	-
Cereplas L810TM	Linear C8/10 trimellitate	90218-76-1	0.973	40	139	49	7.9	129	278	-48	0.05	285	0.05	-
Cereplas OTM	Tri 2-ethylhexyl trimellitate	3319-31-1	0.988	40	301	86	9.4	82	260	-42	0.05	304	0.05	-
Cereplas IDTM	Tri-Iso-Decyl Trimellitate	36631-30-8	0.970	20	500	126	12	86	272	-39	0.05	82	0.05	-
														-
Cereplas DOS	Bis 2-ethyl hexyl sebacate	122-62-3	0.914	30	23	11.5	3.2	160	224	-63	0.01	266	0.05	-
Cereplas DIDS	Di isodecyl sebacate	28473-19-0	0.906	20	42	19	4.7	172	252	-54	0.01	230	0.05	-
Oxube L9-TMP	TMP nC9	126-57-8	0.940	50	-	21	4.5	142	250	-45	0.05	-	0.03	95
Greenfad 21100	TMP 810	91050-89-4	0.940	-	-	20	4.5	137	255	<-50	<0.1	<320	<0.05	85
Greenfad 21120	Complex TMP 810 polymer	-	0.975	-	-	220	20	130	275	-30	<0.5	-	-	-
Greenfad 21140	Complex TMP 810 polymer	-	0.975	-	-	460	40	158	275	-25	<0.5	-	<0.05	83
Greenfad 2130V	TMP trioleate 46	68002-78-8	0.920	-	-	46	>8.5	180	>300	<-40	<1.0	<188	<0.1	-
Greenfad 2100V	TMP trioleate 68	91001-61-5	0.930	-	-	68	>11.28	180	-	<-35	<1.0	-	<0.1	-
Greenfad 2175	TMP trioleate 1500	-	0.990	-	-	1500	-	-	-	<-10	<2.0	-	<0.1	61
Greenfad 2710	MCT / Glycerides 810	73398-61-5		-	-	15	-	135	272	-33	0.1	-	-	>80

To the best of our knowledge, information contained in this datasheet is accurate. However, we do not assume any liability whatsoever for the accuracy and completeness of such information. The customer is responsible for the appropriate safe and legal use, processing and handling of our products. No liability can be accepted in respect of the use of Boester or other products sold or supplied under the brands of other suppliers by Boedal Ltd, alone or in conjunction with other materials. The information contained herein relates exclusively to our products when not used in conjunction with any third party materials. Boedal 2020 all rights reserved.

Boedal

Typical Properties

Product name	Chemical name	CAS No	Density @ 20°C g/cm ³	Colour (H.U.)	Viscosity (ASTM D445) (MM ² /S)			Viscosity Index	Flash point °C COC	Pour point °C	Acid value {mgKOH/g}	SAP value {mgKOH/g}	Water content (% W/W)	OECD301B
					20°C	40°C	100°C							
BRO 2	Blown rapeseed oil	95193-59-2	-	-	-	97	-	-	-	-	3.14	-	-	
BRO 9	Blown rapeseed oil	95193-59-2	-	-	-	304	35	160	271	-18	-	-	-	
BRO 20	Blown rapeseed oil	95193-59-2	-	-	-	584	54	154	255	-15	-	-	-	
BRO 26	Blown rapeseed oil	95193-59-2	-	-	-	726	60	148	217	-12	12 max	-	-	
BRO 35	Blown rapeseed oil	95193-59-2	-	-	-	922	78	163	273	-15	12 max	-	-	
BRO 50	Blown rapeseed oil	95193-59-2	-	-	-	1436	106	163	243	-9	-	-	-	
BRO 90	Blown rapeseed oil	95193-59-2	-	-	-	2562	169	176	251	-3	-	-	-	56

Product name	Chemical name	CAS No	Chlorine content %	Dennsity @ 25°C g/cm ³	Viscosity (ASTM D445) (MM ² /S)			Viscosity Index	Flash point °C COC	Pour point °C	Colour (H.U.)	SAP value {mgKOH/g}	Water content (% W/W)	
					20°C	40°C	100°C							
Cereclor E45	Chlorinated paraffin C14-17	85535-85-9	45	1.12	244	52	8	116	None	-31	150	-	-	
Cereclor E56	Chlorinated paraffin C14-17	85535-85-9	56	1.30	24931	1545	19	-470	None	-8	250	-	-	
Cereclor E60	Chlorinated paraffin C14-17	85535-85-9	60	1.39	117314	7747	55	-229	None	7	250	-	-	
Cereclor S52	Chlorinated paraffin C14-17	85535-85-9	52	1.25	2039	310	15	-9	None	-9	175	-	-	
Cereclor 42	Chlorinated wax C26+	63449-39-8	42	1.16	3500	630	32	74	None	-15	350	-	-	
Cereclor 42SS	Chlorinated wax C26+	63449-39-8	42	1.16	3500	630	32	74	None	-15	250	-	-	
Cereclor 48	Chlorinated wax C26+	63449-39-8	48	1.24	43408	4479	71	17	None	10	500	-	-	

To the best of our knowledge, information contained in this datasheet is accurate. However, we do not assume any liability whatsoever for the accuracy and completeness of such information. The customer is responsible for the appropriate safe and legal use, processing and handling of our products. No liability can be accepted in respect of the use of Boester or other products sold or supplied under the brands of other suppliers by Boedal Ltd, alone or in conjunction with other materials. The information contained herein relates exclusively to our products when not used in conjunction with any third party materials. Boedal 2020 all rights reserved.